

CORDUROY - A PILE WEAVE

Frances A. Morgan


The pile of corduroy, a weft pile fabric, is formed with the pattern weft yarns. The weft floats that go across the fabric in a straight line are cut to form the pile. Each float must be separated by a tabby area. The overshot weft or floats are usually on the top side of the fabric, though in some threadings and treadlings they may be on both sides. The floats may be cut any desired length, depending on the length of the overshot and the design of the material. Try cutting some in different lengths for interesting design and effects. A powerloomed corduroy textile leaves the loom as a flat fabric. The floats are cut in the center of each overshot after it is taken off the loom. However, cutting floats while your weaving is on the loom is much easier and you are less apt to cut into the background yarns. Weave a few inches and then cut floats with your loom at normal weaving tension. Experiment and try both ways.

- CORDUROY: 1. In some treadlings after the floats are cut the ground or tabby areas are usually visible.
 - 2. If warp is closely sett leave some of the floats uncut for a different pattern design. The closer the sett the shorter the floats or warp skips the longer the float the longer the pile.
 - 3. The width and depth (pile) of the floats are controlled by the draft and the treadling. Many overshot threadings may be used for this weave. It is essential that there are tabby areas between the float areas. Otherwise the cut floats will have a tendency to pull out.
 - PILE: 1. The pile may be on one side or both sides of the fabric.
 - 2. It may be the same length on both sides or not.
 - 3. It may be short or long or both on the same side.
 - 4. Pile may be different colors. Try using two or more colors in the same shed.
 - 5. Cut the pile on the loom at your normal weaving tension.
 - 6. Long floats can be left uncut and the textile may be used for draperies or a room divider. Bubble weft making floats two or three times longer. Bubble your weft when making a rug or a bath mat. This makes the pile longer.

Corduroy weave may be used for decorative skirts, skirt borders, bedspreads, couch covers, draperies, room dividers, upholstery, pillows, bath mats, rugs and bags.

Threading

Tie-up



There are 26 threads in the above threading. With a single tie-up these treadlings are possible. The floats will be on the top of your weaving.

Counter Balance Loom

14, 134, 124, 123, and 234

12 and 34 floats are on both sides.

Tabby is 13 and 24.

Jack Loom

1, 2, 3, 4, and 23

12 and 34 floats are on both sides.

Tabby is 13 and 24.

There are ten treadling combinations.

14-234, 14-123, 14-124, 123-124, 14-134 134-123, 124-234, 124-134, 234-134, 123-234. 23-1, 23-4, 23-3, 23-2, 4-3, 2-4,

3-1, 3-2, 1-2, 4-1.

The following treadlings are for swivel weave used in some of the samples.

1, 2, 3, 4, and 23

234, 134, 124, and 14

With a corduroy threading your treading for swivel will be the opposite to corduroy so your floats will be on the bottom of your fabric.

The floats or overshots in this draft go over as many as 19 warp threads and as few as 6 depending upon the treadling used. The weft must also form a tabby with the warp between floats. As many as 17 warp threads are involved in the tabby between the floats and as few as 7 depending upon the treadling used.

Example: 124) weft goes over 19 warp threads

134)

14 weft goes over 6 warp threads

123) 234) 17 warp threads between each float.

124 7 warp threads between each float.

SAMPLE 1

(Shown on cover, bottom row, right.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Black 441.

WEFT: Lily Art. 120, Sports Yarn, Black 2 for tabby and

Lily Art. 130, Knitting Worsted, Scarlet 98 and White 1 for pattern.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom

Counter Balance Loom

Tabby 6 shots — end 24 *4 white wool

13 black 4 white wool 24 black

34 Use red double

13 black 4 white wool 24 black

4 white wool

Tabby 6 shots - end 24

1 white wool 13 black 1 white wool 24 black

12 Use red double 13 black

1 white wool
24 black
1 white wool

Tabby 6 shots — end 24

*Repeat

Jack Loom

Tabby 6 shots — end 13

*123 white wool 24 black

123 white 13 black

12 Use red double

24 black

123 white wool

13 black

123 white wool

Tabby 6 shots — end 13

234 white wool 24 black 234 white wool

13 black

34 Use red double

24 black 234 white wool 13 black 234 white wool

Tabby 6 shots - end 13

*Repeat

SAMPLE 2

(Shown on cover, top row, left.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Black 441.

WEFT: Lily Art. 120, Sports Yarn, Black 2 for tabby and

Lily Art. 130, Knitting Worsted, Scarlet 98 and White 1 for pattern.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom

Jack Loom

*14 white wool Two tabby shots between each

pattern shot — repeat 4 times

3 red wool

Two tabby shots between each pattern shot — repeat 3 times

14 white wool

Two tabby shots — repeat 4 times

2 red wool

Two tabby shots — repeat 3 times

*Repeat

*23 white wool

Two tabby shots between each pattern shot — repeat 4 times

124 red wool

Two tabby shots between each pattern shot—repeat 3 times

23 white wool

Two tabby shots — repeat 4 times

134 red wool

Two tabby shots — repeat 3 times

*Repeat

SAMPLE 3

(Shown on cover, third row, left.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Black 441.

WEFT: Lily Art. 120, Sports Yarn, Black 2 for tabby and Lily Art. 130, Knitting Worsted, Yellow 10 for pattern.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom **Jack Loom** *4 yellow wool *123 yellow wool 13 black

Repeat 6 times using alternate tabby

between pattern shots.

234 yellow wool 13 black

Repeat 6 times using alternate tabby shots between pattern shots.

*Repeat

24 black

Repeat 6 times using alternate tabby between pattern shots.

1 yellow wool 24 black

Repeat 6 times using alternate tabby

between pattern shots.

*Repeat

SAMPLE 4

(Shown on cover, second row, right.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Black 441. WEFT: Lily Art. 130, Knitting Worsted, Emerald 62 for tabby and Emerald 2, used double, and Yellow 10 used single for pattern.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom Jack Loom *12 emerald double *34 emerald double 13 emerald single 24 emerald single 12 emerald double 34 emerald double 24 emerald single 13 emerald single 3 yellow 124 yellow 13 emerald single 24 emerald single 3 yellow 124 yellow 24 emerald single 13 emerald *Repeat *Repeat

SAMPLE 5

(Shown on cover, bottom row, left.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 5/2, Old Gold 79.

WEFT: Lily Art. 114, Floss, Old Gold 79 for tabby and the following yarns on the same shuttle for pattern weft:

> Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Old Gold 79 Lily Art. 114, Mercerized Pearl Cotton, size 10/2, Yellow 404 Lily Art. 130, Knitting Worsted, White 1 and Yellow 10

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom		Jack Loom
(*124 pattern ((13 ((24	Repeat 7 times	(*3 pattern ((24 ((13
10 tabby shots		10 tabby shots
(134 pattern ((13 ((24	Repeat 7 times	(2 pattern ((24 ((13
10 tabby shots		10 tabby shots
*Repeat		*Repeat

SAMPLE 6

(Shown on cover, third row, right.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 5/2, Old Gold 79

WEFT: Lily Art. 114, Floss, Old Gold 79 for tabby and

Lily Art. 130, Knitting Worsted, White 1 for pattern weft.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom		Jack Loom
(*234 pattern		(*1 pattern
((
(13	Repeat 5 times	(24
((
(24		(13
(4 pattern		(123 pattern
((
(13	Repeat 3 times	(24
((
(24		(13
(123 pattern		(4 pattern
((
(13	Repeat 5 times	(24
((
(24		(13
(1 pattern		(234 pattern
((
(13	Repeat 3 times	(24
((
(24		(13
*Repeat		*Repeat

SAMPLE 7

(Shown on cover, second row, left.)

MATERIALS:

WARP: Lily Art. 114, Mercedized Pearl Cotton, size 5/2, Oid Gold 79.

WEFT: Lily Art. 114, Floss, Old Gold 79 for tabby and

Lily Art. 130, Knitting Worsted, White 1 and Yellow 10 for pattern weft.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom Jack Loom

(*134 pattern yellow (*2 pattern yellow

(234 pattern white Repeat 4 times (1 pattern white

(134 pattern yellow (2 pattern yellow

(

(tabby 3 times (tabby 3 times

10 tabby shots between each pattern unit.

*Repeat

*Repeat

SAMPLE 8

(Shown on cover, top row, right.)

MATERIALS:

WARP: Lily Art. 114, Mercerized Pearl Cotton, size 5/2, Old Gold 79

WEFT: Lily Art. 114, Mercerized Pearl Cotton, size 3/2, Old Gold 79 for tabby and

Lily Art. 130, Knitting Worsted, White 1 and Emerald 62 for pattern weft.

Warp set 18 threads to the inch. Use a 9 dent reed — double sley.

Treadling for a Counter Balance Loom Jack Loom

(*123 emerald wool

(Repeat 4 times (

(Tabby 2 times (Tabby 2 times

Tabby 3 times between each pattern unit

(3 white wool (124 white wool

(Repeat 6 times (

(Tabby 2 times (Tabby 2 times

Tabby 3 times between each pattern unit

*Repeat *Repeat

The Handweaver's Headquarters

LILY MILLS COMPANY • Shelby, North Carolina